Mechanics of Materials in SI Units Global Edition 10th Edition Hibbeler Solutions Manual © 2017 Pearson Education, Inc., Hoboken, NJ. All rights reserved. This material is protected under all copyright laws as they currently exist. Full Download Natapasto/adi tabadionanlog@ccopn/pucdulet/mathaniosaof manterials.

3-1.

A tension test was performed on a steel specimen having an original diameter of 0.503 in. and gage length of 2.00 in. The data is listed in the table. Plot the stress-strain diagram and determine approximately the modulus of elasticity, the yield stress, the ultimate stress, and the fracture stress. Use a scale of 1 in. = 20 ksi and 1 in. = 0.05 in./in. Redraw the elastic region, using the same stress scale but a strain scale of 1 in. = 0.001 in./in.

SOLUTION

 $A = \frac{1}{4}\pi (0.503)^2 = 0.1987 \text{ in}^2$



	140
This sample only, Download all chapters at: Aliba	baDownload.com

Load (kip)	Elongation (in.)
0	0
1.50	0.0005
4.60	0.0015
8.00	0.0025
11.00	0.0035
11.80	0.0050
11.80	0.0080
12.00	0.0200
16.60	0.0400
20.00	0.1000
21.50	0.2800
19.50	0.4000
18.50	0.4600

3–2.

Data taken from a stress-strain test for a ceramic are given in the table. The curve is linear between the origin and the first point. Plot the diagram, and determine the modulus of elasticity and the modulus of resilience.

σ (ksi)	ε (in./in.)
0	0
33.2	0.0006
45.5	0.0010
49.4	0.0014
51.5	0.0018
53.4	0.0022

SOLUTION

Modulus of Elasticity: From the stress-strain diagram

$$E = \frac{33.2 - 0}{0.0006 - 0} = 55.3(10^3) \text{ ksi}$$
 Ans.

Modulus of Resilience: The modulus of resilience is equal to the area under the *linear portion* of the stress–strain diagram (shown shaded).



Ans:

$$E = 55.3(10^3)$$
 ksi, $u_r = 9.96 \frac{\text{in} \cdot \text{lb}}{\text{in}^3}$

σ (ksi) ε (in./in.) 0 0 33.2 0.0006 45.5 0.0010 49.4 0.0014 51.5 0.0018 53.4 0.0022

SOLUTION

3–3.

Modulus of Toughness: The modulus of toughness is equal to the area under the stress–strain diagram (shown shaded).

$$(u_t)_{approx} = \frac{1}{2} (33.2) (10^3) \left(\frac{lb}{in^2}\right) (0.0004 + 0.0010) \left(\frac{in.}{in.}\right) + 45.5 (10^3) \left(\frac{lb}{in^2}\right) (0.0012) \left(\frac{in.}{in.}\right) + \frac{1}{2} (7.90) (10^3) \left(\frac{lb}{in^2}\right) (0.0012) \left(\frac{in.}{in.}\right) + \frac{1}{2} (12.3) (10^3) \left(\frac{lb}{in^2}\right) (0.0004) \left(\frac{in.}{in.}\right) = 85.0 \frac{in \cdot lb}{in^3}$$

Data taken from a stress-strain test for a ceramic are given

in the table. The curve is linear between the origin and the first point. Plot the diagram, and determine approximately the

modulus of toughness. The fracture stress is $\sigma_f = 53.4$ ksi.



Ans.

ort Univer and

ard sponter and assessing and spontation and sponter and any article and artic

Ans:

$$(u_t)_{\text{approx}} = 85.0 \frac{\text{in} \cdot \text{lb}}{\text{in}^3}$$

*3-4.

The stress-strain diagram for a steel alloy having an original diameter of 0.5 in. and a gage length of 2 in. is given in the figure. Determine approximately the modulus of elasticity for the material, the load on the specimen that causes yielding, and the ultimate load the specimen will support.

σ (ksi) 80 70 60 50 40 30 20 10 ϵ (in./in.) 0 0 Ans.

Ans.

SOLUTION

Modulus of Elasticity: From the stress–strain diagram, $\sigma = 40$ ksi when $\epsilon = 0.001$ in./in.

$$E_{\text{approx}} = \frac{40 - 0}{0.001 - 0} = 40.0(10^3) \text{ ksi}$$

Yield Load: From the stress–strain diagram, $\sigma_Y = 40.0$ ksi.

$$P_Y = \sigma_Y A = 40.0 \left[\left(\frac{\pi}{4} \right) (0.5^2) \right] = 7.85 \text{ kip}$$

The MORE POLECTED

Ultimate Load: From the stress–strain diagram, $\sigma_u = 76.25$ ksi.

$$P_{u} = \sigma_{u}A = 76.25 \left[\left(\frac{\pi}{4} \right) (0.5^{2}) \right] = 15.0 \text{ kip} Ans.$$

Ans:

$$E_{approx} = 40.0 (10^3) \text{ ksi},$$

 $P_Y = 7.85 \text{ kip},$
 $P_u = 15.0 \text{ kip}$

3-5.

The stress-strain diagram for a steel alloy having an original diameter of 0.5 in. and a gage length of 2 in. is given in the figure. If the specimen is loaded until it is stressed to 70 ksi, determine the approximate amount of elastic recovery and the increase in the gage length after it is unloaded.

σ (ksi) 80 70 60 50 40 30 20 10 ϵ (in./in.) 0 0 Ans Just Health of the net received Uncounter of Both Bernite

SOLUTION

Modulus of Elasticity: From the stress–strain diagram, $\sigma = 40$ ksi when $\epsilon = 0.001$ in./in.

$$E = \frac{40 - 0}{0.001 - 0} = 40.0(10^3) \text{ ksi}$$

Elastic Recovery:

Elastic recovery
$$=\frac{\sigma}{E} = \frac{70}{40.0(10^3)} = 0.00175$$
 in./in.

Thus,

The amount of Elastic Recovery = 0.00175(2) = 0.00350 in.

Permanent Set:

Permanent set = 0.08 - 0.00175 = 0.07825 in./in.

Thus,

Permanent elongation = 0.07825(2) = 0.1565 in. or sale of any part of the work of the ' MORT LIE WOR POWERS Trell OUTSS and Basesonning

and the formation of the states

3-6.

The stress–strain diagram for a steel alloy having an original diameter of 0.5 in. and a gage length of 2 in. is given in the figure. Determine approximately the modulus of resilience and the modulus of toughness for the material.



SOLUTION

Modulus of Resilience: The modulus of resilience is equal to the area under the *linear portion* of the stress–strain diagram.

$$(u_r)_{\text{approx}} = \frac{1}{2} (40.0) (10^3) \left(\frac{\text{lb}}{\text{in}^2}\right) \left(0.001 \frac{\text{in.}}{\text{in.}}\right) = 20.0 \frac{\text{in} \cdot \text{lb}}{\text{in}^3}$$

Modulus of Toughness: The modulus of toughness is equal to the total area under the stress–strain diagram and can be approximated by counting the number of squares. The total number of squares is 45.

$$(u_t)_{approx} = 45 \left(10 \frac{\text{kip}}{\text{in}^2} \right) \left(0.04 \frac{\text{in}}{\text{in}} \right) = 18.0 \frac{\text{in} \cdot \text{kip}}{\text{in}^3}$$
Ans.

Ans:

 $(u_r)_{\text{approx}} = 20.0 \frac{\text{in} \cdot \text{lb}}{\text{in}^3},$ $(u_t)_{\text{approx}} = 18.0 \frac{\text{in} \cdot \text{kip}}{\text{in}^3}$

3–7.

SOLUTION

 $+\Sigma M_C = 0; \qquad F_{AB} \sin 30^{\circ}(10)$

The rigid beam is supported by a guy wire AB. If the wire has a dia how much it stretches when a distr acts on the beam. The material re

Ans: $\delta_{AB} = 0.152$ in.

*3-8.

The rigid beam is supported by a pin at C and an A-36 steel guy wire AB. If the wire has a diameter of 0.2 in., determine the distributed load w if the end B is displaced 0.75 in. downward.

SOLUTION



their ourses



Ans.

Ans.

3-9.

Acetal plastic has a stress-strain diagram as shown. If a bar of this material has a length of 3 ft and cross-sectional area of 0.875 in², and is subjected to an axial load of 2.5 kip, determine its elongation.



SOLUTION

 $\sigma = \frac{P}{A} = \frac{2.5}{0.875} = 2.857$ ksi

 $\sigma = 9.5(10^3)\epsilon^{1/3}$

 $2.857(10^3) = 9.5(10^3)\epsilon^{1/3}$

 $\epsilon = 0.0272$ in./in.

 $\delta = L\epsilon = 3(12)(0.0272) = 0.979$ in.

Ans: $\delta = 0.979$ in.

of sale of any participation of the work and is not particle of the integrity of the work and is not particle of the work and

their courses and assessing student earth of the more and assessing student earth of the more and the more an

I TO NOT POWER ON A SOLAR SOLA althe store of the state

This work is !

und see here

3-10.

The stress-strain diagram for an aluminum alloy specimen having an original diameter of 0.5 in. and a gage length of 2 in. is given in the figure. Determine approximately the modulus of elasticity for the material, the load on the specimen that causes yielding, and the ultimate load the specimen will support.



Ans.

SOLUTION

Modulus of Elasticity: From the stress-strain diagram, $\sigma = 50.0$ ksi when $\epsilon = 0.005$ in./in. Thus

$$E_{\text{approx}} = \frac{50.0 - 0}{0.005 - 0} = 10.0(10^3) \text{ ksi}$$
 Ans.

Yield Load: From the stress–strain diagram, $\sigma_v = 50.0$ ksi. Thus

$$P_Y = \sigma_y A = 50.0 \left[\frac{\pi}{4} (0.5^2) \right] = 9.82 \text{ kip}$$

Ultimate Load: From the stress–strain diagram, $\sigma_u = 68.0$ ksi. Thus,

$$P_u = \sigma_u A = 68.0 \left[\frac{\pi}{4} (0.5^2) \right] = 13.4 \text{ kip}$$

$$P_{u} = \sigma_{u}A = 68.0 \left[\frac{\pi}{4}(0.5^{2})\right] = 13.4 \text{ kip}$$

$$D(ksi)$$

$$D($$

Ans: $E_{\rm approx} = 10.0(10^3) \, \rm ksi,$ $P_Y = 9.82 \text{ kip},$ $P_u = 13.4 \, \text{kip}$

in teaching

Ans.

3–11.

The stress-strain diagram for an aluminum alloy specimen having an original diameter of 0.5 in. and a gage length of 2 in. is given in the figure. If the specimen is loaded until it is stressed to 60 ksi, determine the approximate amount of elastic recovery and the increase in the gage length after it is unloaded.



SOLUTION

Modulus of Elasticity: From the stress-strain diagram, $\sigma = 50.0$ ksi when $\epsilon = 0.005$ in./in. Thus

$$E_{\text{approx}} = \frac{50.0 - 0}{0.005 - 0} = 10.0(10^3) \text{ ksi}$$

Elastic Recovery and Permanent Set: From the stress-strain diagram, $\sigma = 60$ ksi when $\epsilon = 0.04$ in./in. Thus

$$\frac{\sigma}{E} = \frac{60}{10.0(10^3)} = 0.006$$
 in./in.

Thus,

Elastic Recovery =
$$(0.006)(2) = 0.012$$
 in

And

Permanent set =
$$0.04 - 0.006 = 0.034$$
 in./in.

Then

Elastic Recovery =
$$(0.006)(2) = 0.012$$
 in. Ans.
Permanent set = $0.04 - 0.006 = 0.034$ in./in,
Permanent elongation = $0.034(2) = 0.0680$ in. Ans.

O(Ksi)



Ans: Elastic recovery = 0.012 in., Permanent elongation = 0.0680 in.

*3-12.

The stress-strain diagram for an aluminum alloy specimen having an original diameter of 0.5 in. and a gage length of 2 in. is given in the figure. Determine approximately the modulus of resilience and the modulus of toughness for the material.



SOLUTION

Modulus of Resilience: The modulus of resilience is equal to the area under the linear portion of the stress-strain diagram.

$$(u_r)_{\text{approx}} = \frac{1}{2} [50.0(10^3) \text{lb/in}^2] (0.005 \text{ in./in.}) = 125 \frac{\text{in} \cdot \text{lb}}{\text{in}^3}$$
 Ans.

Modulus of Toughness: The modulus of toughness is equal to the entire area under the stress-strain diagram, which can be approximated by counting the number of squares. The total number of squares is 63.



Ans:

 $(u_r)_{\text{approx}} = 125 \frac{\text{in} \cdot \text{lb}}{\text{in}^3},$ $(u_t)_{\text{approx}} = 12.6 \frac{\text{in} \cdot \text{kip}}{\text{in}^3}$

3-13.

A bar having a length of 5 in. and cross-sectional area of 0.7 in.^2 is subjected to an axial force of 8000 lb. If the bar stretches 0.002 in., determine the modulus of elasticity of the material. The material has linear elastic behavior.



SOLUTION

Normal Stress and Strain:

$$\sigma = \frac{P}{A} = \frac{8.00}{0.7} = 11.43 \text{ ksi}$$
$$\epsilon = \frac{\delta}{L} = \frac{0.002}{5} = 0.000400 \text{ in./in.}$$

Modulus of Elasticity:



3–14.

The rigid pipe is supported by a pin at A and an A-36 steel guy wire *BD*. If the wire has a diameter of 0.25 in., determine how much it stretches when a load of P = 600 lb acts on the pipe.



SOLUTION

Here, we are only interested in determining the force in wire BD. Referring to the FBD in Fig. a

$$\zeta + \Sigma M_A = 0;$$
 $F_{BD}\left(\frac{4}{5}\right)(3) - 600(6) = 0$ $F_{BD} = 1500 \text{ lb}$

The normal stress developed in the wire is

$$\sigma_{BD} = \frac{F_{BD}}{A_{BD}} = \frac{1500}{\frac{\pi}{4} (0.25^2)} = 30.56(10^3) \text{ psi} = 30.56 \text{ ksi}$$

Since $\sigma_{BD} < \sigma_y = 36$ ksi, Hooke's Law can be applied to determine the strain in the wire.

$$\sigma_{BD} = E\epsilon_{BD}; \qquad 30.56 = 29.0(10^3)\epsilon_{BD}$$
$$\epsilon_{BD} = 1.054(10^{-3}) \text{ in./in.}$$

The unstretched length of the wire is $L_{BD} = \sqrt{3^2 + 4^2} = 5$ ft = 60 in. Thus, the wire stretches

$$\delta_{BD} = \epsilon_{BD} L_{BD} = 1.054(10^{-3})(60)$$

= 0.0632 in.

Ans.



3-15.

The rigid pipe is supported by a pin at A and an A-36 guy wire BD. If the wire has a diameter of 0.25 in., determine the load P if the end C is displaced 0.075 in. downward.



SOLUTION

Here, we are only interested in determining the force in wire BD. Referring to the FBD in Fig. a

$$\zeta + \Sigma M_A = 0;$$
 $F_{BD}(\frac{4}{5})(3) - P(6) = 0$ $F_{BD} = 2.50 P$

The unstretched length for wire *BD* is $L_{BD} = \sqrt{3^2 + 4^2} = 5$ ft = 60 in. From the geometry shown in Fig. *b*, the stretched length of wire *BD* is

$$L_{BD'} = \sqrt{60^2 + 0.075^2 - 2(60)(0.075)\cos 143.13^\circ} = 60.060017$$

Thus, the normal strain is

$$\epsilon_{BD} = \frac{L_{BD'} - L_{BD}}{L_{BD}} = \frac{60.060017 - 60}{60} = 1.0003(10^{-3}) \text{ in./in.}$$

Then, the normal stress can be obtain by applying Hooke's Law.

$$\sigma_{BD} = E\epsilon_{BD} = 29(10^3) [1.0003(10^{-3})] = 29.01 \text{ ks}$$

Since $\sigma_{BD} < \sigma_y = 36$ ksi, the result is valid.

formal stress can be obtain by applying Hooke's Law.

$$\sigma_{BD} = E\epsilon_{BD} = 29(10^3) [1.0003(10^{-3})] = 29.01 \text{ ksi}$$

$$< \sigma_y = 36 \text{ ksi, the result is valid.}$$

$$\sigma_{BD} = \frac{F_{BD}}{A_{BD}}; \quad 29.01(10^3) = \frac{2.50 P}{\frac{\pi}{4}(0.25^2)}$$

$$P = 569.57 \text{ lb} = 570 \text{ lb}$$

Ans.

work and





*3–16.

Direct tension indicators are sometimes used instead of torque wrenches to ensure that a bolt has a prescribed tension when used for connections. If a nut on the bolt is tightened so that the six 3-mm high heads of the indicator are strained 0.1 mm/mm, and leave a contact area on each head of 1.5 mm^2 , determine the tension in the bolt shank. The material has the stress–strain diagram shown.

SOLUTION

Stress-Strain Relationship: From the stress-strain diagram with

 $\epsilon\,=\,0.1~\mathrm{mm}/\mathrm{mm}\,>\,0.0015~\mathrm{mm}/\mathrm{mm}$

$$\frac{\sigma - 450}{0.1 - 0.0015} = \frac{600 - 450}{0.3 - 0.0015}$$

$$\sigma = 499.497 \text{ MPa}$$

Axial Force: For each head

$$P = \sigma A = 499.4971(10^6)(1.5)(10^{-6}) = 749.24 \text{ N}$$

Thus, the tension in the bolt is

$$T = 6 P = 6(749.24) = 4495 N = 4.50 kN$$
 Ans.

I. The sponder and as the sponder of the sponder of



work and

3–17.

The rigid beam is supported by a pin at C and an A992 steel guy wire AB of length 6 ft. If the wire has a diameter of 0.2 in., determine how much it stretches when a distributed load of w = 200 lb/ft acts on the beam. The wire remains elastic.

SOLUTION

Support Reactions: Referring to the FBD of the beam, Fig. *a*,

$$\zeta + \Sigma M_C = 0;$$
 $F_{AB} \cos 30^{\circ}(10) - 0.2(10)(5) = 0$ $F_{AB} = 1.1547 \text{ kip}$

Normal Stress and Strain Relation: The normal stress is

$$\sigma_{AB} = \frac{F_{AB}}{A_{AB}} = \frac{1.1547}{\frac{\pi}{4}(0.2^2)} = 36.76 \text{ ksi}$$

For structural A992 steel alloy, $E_{st} = 29.0(10^3)$ ksi.

$$\sigma = E\epsilon; \qquad 36.76 = 29.0(10^3)\epsilon_{AB}$$
$$\epsilon_{AB} = 0.001267 \text{ in./in.}$$

Thus,

$$\delta_{AB} = \epsilon_{AB} L_{AB} = (0.001267 \text{ in./in.}) (72 \text{ in.}) = 0.0913 \text{ in.}$$
 Ans.



Ans: $\delta_{AB} = 0.0913$ in.

30

10 ft

work and

3-18.

The rigid beam is supported by a pin at C and an A992 steel guy wire AB of length 6 ft. If the wire has a diameter of 0.2 in., determine the distributed load w if the end B is displaced 0.12 in. downward. The wire remains elastic.

SOLUTION

Support Reactions: Referring to the FBD of the beam, Fig. *a*,

$$\zeta + \Sigma M_C = 0;$$
 $F_{AB} \cos 30^{\circ}(10) - 10w(5) = 0$ $F_{AB} = \frac{10\sqrt{3}}{3}w$

Normal Stress and Strain Relation: Referring to the geometry shown in Fig. *b*, and applying cosine law and sine law,

$$L_{AC} = \sqrt{10^2 + 6^2} - 2(10)(6) \cos 120^\circ = 14 \text{ ft}$$
$$\frac{\sin \phi}{6} = \frac{\sin 120^\circ}{14}; \qquad \phi = 21.7868^\circ$$
$$\sin \theta = \frac{0.01}{10}; \qquad \theta = 0.05730^\circ$$

Thus,

$$L_{AB'} = \sqrt{14^2 + 10^2 - 2(14)(10)} \cos(21.7868^\circ + 0.05730^\circ) = 6.008665 \text{ ft}$$

Then

$$\epsilon_{AB} = \frac{L_{AB}' - L_{AB}}{L_{AB}} = \frac{6.008665 - 6}{6} = 0.001444$$
 in./in.

For structural A992 steel alloy, $E_{st} = 29.0(10^3)$ ksi. Thus,

$$\sigma_{AB} = E\epsilon_{AB} = 29(10^3)(0.001444) = 41.88 \text{ ksi} < 50 \text{ ksi}$$
(O.K!)
$$F_{AB} = \sigma_{AB}A_{AB}; \quad \frac{10\sqrt{3}}{3}w = (41.88)\left[\frac{\pi}{4}(0.2^2)\right]$$
$$w = 0.2279 \text{ kip/ft} = 228 \text{ lb/ft}$$
Ans.



30

w

10 ft

3-19.

The stress-strain diagram for a bone is shown, and can be described by the equation $\epsilon = 0.45(10^{-6}) \sigma + 0.36(10^{-12}) \sigma^3$, where σ is in kPa. Determine the yield strength assuming a 0.3% offset.

$\epsilon = 0.45(10^{-6})\sigma + 0.36(10^{-12})\sigma$ $= 0.45(10^{-6})\sigma + 0.36(10^{-12})\sigma$

SOLUTION

$$\epsilon = 0.45(10^{-6})\sigma + 0.36(10^{-12})\sigma^3,$$

$$d\epsilon = (0.45(10^{-6}) + 1.08(10^{-12})\sigma^2)d\sigma$$

$$E = \frac{d\sigma}{d\epsilon} \bigg|_{\sigma=0} = \frac{1}{0.45(10^{-6})} = 2.22(10^6) \text{ kPa} = 2.22 \text{ GPa}$$

12.

The equation for the recovery line is $\sigma = 2.22(10^6)(\epsilon - 0.003)$.

- . . - 6.

This line intersects the stress–strain curve at $\sigma_{YS} = 2027 \text{ kPa} = 2.03 \text{ MPa}$

Ans.

orsale of any part of the store of the work and the story the integrity of the work and the story of the stor

IND WAR DUNCH CONTRACT

net out for and a set of the interim all the store of the state of the store of t

work including

*3-20.

The stress-strain diagram for a bone is shown and can be described by the equation $\epsilon = 0.45(10^{-6}) \sigma +$ $0.36(10^{-12}) \sigma^3$, where σ is in kPa. Determine the modulus of toughness and the amount of elongation of a 200-mm-long region just before it fractures if failure occurs at $\epsilon = 0.12$ mm/mm.

SOLUTION

When $\epsilon = 0.12$

$$120(10^{-3}) = 0.45 \sigma + 0.36(10^{-6})\sigma^3$$

Solving for the real root:

$$\sigma = 6873.52 \text{ kPa}$$

$$u_{t} = \int_{A} dA = \int_{0}^{6873.52} (0.12 - \epsilon) d\sigma$$

$$u_{t} = \int_{0}^{6873.52} (0.12 - 0.45(10^{-6})\sigma - 0.36(10^{-12})\sigma^{3}) d\sigma$$

$$= 0.12 \sigma - 0.225(10^{-6})\sigma^{2} - 0.09(10^{-12})\sigma^{4}|_{0}^{687352}$$

$$= 613 \text{ kJ/m}^{3}$$

$$\delta = \epsilon L = 0.12(200) = 24 \text{ mm}$$
Ans.
$$\int_{0}^{2} \frac{\epsilon}{\epsilon} \int_{0}^{2} \frac{1}{\epsilon} \int_{0}^{$$

Ans:

$$u_t = 613 \text{ kJ/m}^3$$

 $\delta = 24 \text{ mm}$

 $\epsilon = 0.45(10^{-6})\sigma + 0.36(10^{-12})\sigma$

3-21.

The two bars are made of a material that has the stressstrain diagram shown. If the cross-sectional area of bar AB is 1.5 in² and BC is 4 in², determine the largest force P that can be supported before any member fractures. Assume that buckling does not occur. **SOLUTION** +↑ $\Sigma F_y = 0;$ $\frac{3}{5}F_{AB} - P = 0;$ $F_{AB} = 1.6667 P$ + $\Sigma F_x = 0;$ $F_{BC} - \frac{4}{5}(1.6667P) = 0;$ $F_{BC} = 1.333 P$ (1) (2) Assuming failure of bar BC: σ (ksi) From the stress–strain diagram $(\sigma_R)_t = 5$ ksi 25 $\sigma = \frac{F_{BC}}{A_{BC}}; \qquad 5 = \frac{F_{BC}}{4};$ $F_{BC} = 20.0 \text{ kip}$ 20 15 From Eq. (2), P = 15.0 kip compression 10 Assuming failure of bar AB: tension 5 From stress–strain diagram $(\sigma_R)_c = 25.0$ ksi 0.60 0.75 $F_{AB} = 37.5 \text{ kip}$ 0.20 0.40 0 $\sigma = \frac{F_{AB}}{A_{AB}}; \qquad 25.0 = \frac{F_{AB}}{1.5};$ From Eq. (1), P = 22.5 kip Choose the smallest value:

wildestroy

 $P = 15.0 \, \text{kip}$

Ans: P = 15.0 kip

 $-\epsilon (10^{-3})$ (in./in.)

X

Ans.

3-22.

The two bars are made of a material that has the stressstrain diagram shown. Determine the cross-sectional area of each bar so that the bars fracture simultaneously when the load P = 3 kip. Assume that buckling does not occur. 3 ft σ (ksi) SOLUTION 25 $+\uparrow \Sigma F_y = 0;$ $F_{BA}\left(\frac{3}{5}\right) - 3 = 0;$ $F_{BA} = 5 \text{ kip}$ 20 $\stackrel{+}{\longrightarrow} \Sigma F_x = 0;$ $-F_{BC} + 5\left(\frac{4}{5}\right) = 0;$ $F_{BC} = 4 \text{ kip}$ 15 compression 10 tension 5 For member *BC*: 0°0 0.60 0.75 0.20 0.40 $(\sigma_{\max})_t = \frac{F_{BC}}{A_{BC}}; \quad A_{BC} = \frac{4 \text{ kip}}{5 \text{ ksi}} = 0.8 \text{ in}^2$ Ans. For member BA: Foc $(\sigma_{\text{max}})_c = \frac{F_{BA}}{A_{BA}}; \quad A_{BA} = \frac{5 \text{ kip}}{25 \text{ ksi}} = 0.2 \text{ in}_c^2$ Ans. 1.1.1.53180. 2014. 01.5.1.80 will destroy the

> Ans: $A_{BC} = 0.8 \text{ in}^2, A_{BA} = 0.2 \text{ in}^2$

 ϵ (10⁻³) (in./in.)

3-23.

The pole is supported by a pin at C and an A-36 steel guy wire AB. If the wire has a diameter of 0.2 in., determine how much it stretches when a horizontal force of 2.5 kip acts on the pole.

This work is

SOLUTION

$$\sigma_{AB} = \frac{F_{AB}}{A_{AB}} = \frac{2.857}{\frac{\pi}{4} (0.2^2)} = 90.94 \text{ ksi}$$

$$\epsilon_{AB} = \frac{\sigma_{AB}}{E} = \frac{90.94}{29(10^3)} = 0.003136$$

$$\delta_{AB} = \epsilon_{AB} L_{AB} = 0.003136 \left(\frac{7(12)}{\cos 30^\circ}\right)$$





Ans: $\delta_{AB} = 0.304$ in.

*3–24.

The bar DA is rigid and is originally held in the horizontal position when the weight W is supported from C. If the weight causes B to displace downward 0.025 in., determine the strain in wires DE and BC. Also, if the wires are made of A-36 steel and have a cross-sectional area of 0.002 in², determine the weight W.

SOLUTION

 $\frac{3}{0.025} = \frac{7}{8}$ $\delta = 0.0417 \text{ in.}$ $\epsilon_{DE} = \frac{\delta}{L} = \frac{0.0417}{3(12)} = 0.00116 \text{ in./in.}$ $\sigma_{DE} = E\epsilon_{DE} = 29(10^3)(0.00116) = 33.56 \text{ ksi}$ $F_{DE} = \sigma_{DE}A_{DE} = 33.56(0.002) = 0.0672 \text{ kip}$ $\zeta + \Sigma M_A = 0; \quad -(0.0672)(5) + 3(W) = 0$ W = 0.112 kip = 112 lb $\sigma_{BC} = \frac{W}{A_{BC}} = \frac{0.112}{0.002} = 55.94 \text{ ksi}$ $\epsilon_{BC} = \frac{\sigma_{BC}}{E} = \frac{55.94}{29(10^3)} = 0.00193 \text{ in./in.}$

0.0417 0.025 *

4 ft

3 ft

Ans.

Ans.

Ans.

D



Ans: - 0.00

 $\begin{aligned} \epsilon_{DE} &= 0.00116 \text{ in./in.,} \\ W &= 112 \text{ lb,} \\ \epsilon_{BC} &= 0.00193 \text{ in./in.} \end{aligned}$

3-25.

The acrylic plastic rod is 200 mm long and 15 mm in diameter. If an axial load of 300 N is applied to it, determine the change in its length and the change in its diameter. $E_{\rm p} = 2.70 \text{ GPa}, \nu_{\rm p} = 0.4.$



SOLUTION

 $\sigma = \frac{P}{A} = \frac{300}{\frac{\pi}{4}(0.015)^2} = 1.678 \text{ MPa}$ $\epsilon_{\text{long}} = \frac{\sigma}{E} = \frac{1.678(10^6)}{2.70(10^9)} = 0.0006288$ $\delta = \epsilon_{\text{long}} L = 0.0006288(200) = 0.126 \text{ mm}$

Ans.

Ans.

 $\epsilon_{\text{lat}} = -\nu\epsilon_{\text{long}} = -0.4(0.0006288) = -0.0002515$

 $\Delta d = \epsilon_{\text{lat}} d = -0.0002515(15) = -0.00377 \text{ mm}$

Ans: $\delta = 0.126 \text{ mm}, \Delta d = -0.00377 \text{ mm}$

Hel OUSES and assessing All Phones and a

and 5 portided

or sale of any part of the shift's

Ans.

Ans.

3-26.

The plug has a diameter of 30 mm and fits within a rigid sleeve having an inner diameter of 32 mm. Both the plug and the sleeve are 50 mm long. Determine the axial pressure p that must be applied to the top of the plug to cause it to contact the sides of the sleeve. Also, how far must the plug be compressed downward in order to do this? The plug is made from a material for which E = 5 MPa, $\nu = 0.45$.

SOLUTION

$\epsilon_{\text{lat}} = \frac{d' - d}{d} = \frac{32 - 30}{30} = 0.06667 \text{ mm/mm}$		
$v = -\frac{\epsilon_{\text{lat}}}{\epsilon_{\text{long}}};$ $\epsilon_{\text{long}} = -\frac{\epsilon_{\text{lat}}}{v} = -\frac{0.06667}{0.45} = -0.1481 \text{ mm/mm}$		
$p = \sigma = E \epsilon_{\text{long}} = 5(10^6)(0.1481) = 741 \text{ kPa}$		

$$\delta = |\epsilon_{\text{long}}L| = |-0.1481(50)| = 7.41 \text{ mm}$$



Hel cause and as of the work and is not permitted. of sale of any part of the and of the work and 5 not performed

This work is projected by United States copylight, in the states of the and is policed and as of this work (not the of the second decision o

3-27.

The elastic portion of the stress-strain diagram for an aluminum alloy is shown in the figure. The specimen from which it was obtained has an original diameter of 12.7 mm and a gage length of 50.8 mm. When the applied load on the specimen is 50 kN, the diameter is 12.67494 mm. Determine Poisson's ratio for the material.



SOLUTION

Average Normal Stress:

$$\sigma = \frac{N}{A} = \frac{50(10^3)}{\frac{\pi}{4}(0.0127^2)} = 394.71(10^6) \text{ Pa} = 394.71 \text{ MPa}$$

Average Normal Strain: Referring to the stress-strain diagram, the modulus of

elasticity is
$$E = \frac{490(10^{\circ})}{0.007} = 70.0(10^{\circ})$$
 Pa = 70.0 GPa.
 $\epsilon_{\text{long}} = \frac{\sigma}{E} = \frac{394.71(10^{\circ})}{70.0(10^{\circ})} = 0.0056386 \text{ mm/mm}$
 $\epsilon_{\text{lat}} = \frac{d - d_0}{d_0} = \frac{12.67494 - 12.7}{12.7} = -0.0019732$

Poisson's Ratio: The lateral and longitudinal strain can be related using Poisson's ratio, that is Hell Courses and assessing the of the art of the original sector and the sector of the original sector of the orig or sale of any part of the interity of the In the second se and a point and and a strain an

$$\nu = -\frac{\epsilon_{\text{lat}}}{\epsilon_{\text{long}}} = -\frac{(-0.019732)}{0.0056386} = 0.350$$

Ans.

*3-28.

The elastic portion of the stress-strain diagram for an aluminum alloy is shown in the figure. The specimen from which it was obtained has an original diameter of 12.7 mm and a gage length of 50.8 mm. If a load of P = 60 kN is applied to the specimen, determine its new diameter and length. Take $\nu = 0.35$.

σ (MPa) 490 $-\epsilon (mm/mm)$ 0.007

SOLUTION

Average Normal Stress:

$$\sigma = \frac{N}{A} = \frac{60(10^3)}{\frac{\pi}{4}(0.0127^2)} = 473.65(10^6) \text{ Pa} = 473.65 \text{ MPa}$$

Average Normal Strain: Referring to the stress-strain diagram, the modulus of

elasticity is
$$E = \frac{490(10^6)}{0.007} = 70.0(10^9)$$
 Pa = 70.0 GPa.
 $\sigma = \frac{473.65(10^6)}{10^6}$

$$\epsilon_{\text{long}} = \frac{\sigma}{E} = \frac{475.03(10^{\circ})}{70.0(10^{\circ})} = 0.0067664 \text{ mm/mm}$$

Thus,

$$\delta L = \epsilon_{\text{long}} L_0 = 0.0067664(50.8) = 0.34373 \text{ mm}$$

Then

is,

$$\delta L = \epsilon_{\text{long}} L_0 = 0.0067664(50.8) = 0.34373 \text{ mm}$$

in
 $L = L_0 + \delta L = 50.8 + 0.34373 = 51.1437 \text{ mm}$

Poisson's Ratio: The lateral strain can be related to the longitudinal strain using Poisson's ratio. Sideo and art of 14. is

$$\epsilon_{\text{lat}} = -\nu\epsilon_{\text{long}} = -0.35(0.0067664) = -0.0023682 \text{ mm/mm}$$

Thus,

 $\delta d = \epsilon_{\text{lat}} d = -0.0023682(12.7) = -0.030077 \text{ mm}$

Then

 $d = d_0 + \delta d = 12.7 + (-0.030077) = 12.66992 \text{ mm}$

Ans.

Ans.

Ans: L = 51.1437 mm,d = 12.67 mm

3-29.

The brake pads for a bicycle tire are made of rubber. If a frictional force of 50 N is applied to each side of the tires, determine the average shear strain in the rubber. Each pad has cross-sectional dimensions of 20 mm and 50 mm. $G_{\rm r} = 0.20$ MPa.



SOLUTION

Average Shear Stress: The shear force is V = 50 N.

$$\tau = \frac{V}{A} = \frac{50}{0.02(0.05)} = 50.0 \text{ kPa}$$

Shear-Stress - Strain Relationship: Applying Hooke's law for shear

$$\tau = G \gamma$$

$$50.0(10^3) = 0.2(10^6) \gamma$$

$$\gamma = 0.250 \text{ rad}$$

ath of color to on the the Inswind Bridden order

> Ans: $\gamma = 0.250$ rad

 $\frac{P}{2}$

 τ (ksi)

75

50

0.005

(a)

3-30.

The lap joint is connected together using a 1.25 in. diameter bolt. If the bolt is made from a material having a shear stress-strain diagram that is approximated as shown, determine the shear strain developed in the shear plane of the bolt when P = 75 kip.

SOLUTION

Internal Loadings: The shear force developed in the shear planes of the bolt can be determined by considering the equilibrium of the free-body diagram shown in Fig. *a*.

 $\stackrel{+}{\to} \Sigma F_x = 0;$ 75 - 2V = 0 V = 37.5 kip

Shear Stress and Strain:

$$\tau = \frac{V}{A} = \frac{37.5}{\frac{\pi}{4} (1.25^2)} = 30.56 \text{ ksi}$$

Using this result, the corresponding shear strain can be obtained from the shear stress-strain diagram, Fig. b.

$$\frac{30.56}{\gamma} = \frac{50}{0.005}; \qquad \gamma = 3.06(10^{-3}) \text{ rad}$$

$$\gamma = 3.06(10^{-3}) \text{ rad}$$

75

50

20.005 Y

(6)

T=30.56

Ans:
$$\gamma = 3.06(10^{-3})$$
 rad

Y(rad

 γ (rad)

5 Kips

0.05

3-31.

The lap joint is connected together using a 1.25 in. diameter bolt. If the bolt is made from a material having a shear stress-strain diagram that is approximated as shown, determine the permanent shear strain in the shear plane of the bolt when the applied force P = 150 kip is removed.



SOLUTION

Internal Loadings: The shear force developed in the shear planes of the bolt can be determined by considering the equilibrium of the free-body diagram shown in Fig. a.

$$\pm \Sigma F_x = 0;$$
 150 - 2V = 0 V = 75 kip

Shear Stress and Strain:

$$\tau = \frac{V}{A} = \frac{75}{\frac{\pi}{4} (1.25^2)} = 61.12 \text{ ksi}$$

Using this result, the corresponding shear strain can be obtained from the shear stress–strain diagram, Fig. *b*.

 $\frac{61.12 - 50}{\gamma - 0.005} = \frac{75 - 50}{0.05 - 0.005}; \qquad \gamma = 0.02501 \text{ rad}$

When force **P** is removed, the shear strain recovers linearly along line BC, Fig. b, with a slope that is the same as line OA. This slope represents the shear modulus.

$$G = \frac{50}{0.005} = 10(10^3) \, \mathrm{ksi}_{\mathrm{sc}}$$

Thus, the elastic recovery of shear strain is

$$\tau = G\gamma_r;$$
 61.12 = (10)(10³) γ_r $\gamma_r = 6.112(10^{-3})$ rad

And the permanent shear strain is

 $\gamma_P = \gamma - \gamma_r = 0.02501 - 6.112(10^{-3}) = 0.0189 \text{ rad}$ Ans.



*3-32. The rubber block is subjected to an elongation of 0.03 in. v along the x axis, and its vertical faces are given a tilt so that $\theta = 89.3^{\circ}$. Determine the strains ϵ_x , ϵ_y and γ_{xy} . Take $\nu_r = 0.5$. 3 in. 4 in. SOLUTION $\epsilon_x = \frac{\delta L}{L} = \frac{0.03}{4} = 0.0075 \text{ in./in.}$ Ans. $\epsilon_y = -\nu \epsilon_x = -0.5(0.0075) = -0.00375$ in./in. Ans. $\gamma_{xy} = \frac{\pi}{2} - \theta = \frac{\pi}{2} - 89.3^{\circ} \left(\frac{\pi}{180^{\circ}}\right) = 0.0122 \text{ rad}$ Ans. of safe of any part of the work including on the rol of one work and a store the inequiry of the work and a rol of the store work and a rol of In the provided solution of the solution of th Del Cultes all ase they at the cure and are a Ans: $\epsilon_x = 0.0075 \text{ in./in.},$ $\epsilon_y = -0.00375$ in./in., $\dot{\gamma_{xy}} = 0.0122$ rad

3-33.

The shear stress–strain diagram for an alloy is shown in the figure. If a bolt having a diameter of 0.25 in. is made of this material and used in the lap joint, determine the modulus of elasticity *E* and the force *P* required to cause the material to yield. Take $\nu = 0.3$.



SOLUTION

Modulus of Rigidity: From the stress-strain diagram,

$$G = \frac{50}{0.004} = 12.5(10^3) \text{ ksi}$$

Modulus of Elasticity:

$$G = \frac{E}{2(1 + \nu)}$$

12.5(10³) = $\frac{E}{2(1 + 0.3)}$
 $E = 32.5(10^3)$ ksi

Yielding Shear: The bolt is subjected to a yielding shear of $V_{\gamma} = P$. From the stress-strain diagram, $\tau_{\gamma} = 50$ ksi



Ans

Ans: $E = 32.5(10^3)$ ksi, P = 2.45 kip

3–34.

A shear spring is made from two blocks of rubber, each having a height h, width b, and thickness a. The blocks are bonded to three plates as shown. If the plates are rigid and the shear modulus of the rubber is G, determine the displacement of plate A when the vertical load **P** is applied. Assume that the displacement is small so that $\delta = a \tan \gamma \approx a\gamma$.

SOLUTION

Average Shear Stress: The rubber block is subjected to a shear force of $V = \frac{P}{2}$.

$$\tau = \frac{V}{A} = \frac{\frac{P}{2}}{bh} = \frac{P}{2bh}$$

Shear Strain: Applying Hooke's law for shear

$$\gamma = \frac{\tau}{G} = \frac{\frac{P}{2bh}}{G} = \frac{P}{2bhG}$$

Thus,





R3-1.

The elastic portion of the tension stress-strain diagram for an aluminum alloy is shown in the figure. The specimen used for the test has a gage length of 2 in. and a diameter of 0.5 in. When the applied load is 9 kip, the new diameter of the specimen is 0.49935 in. Calculate the shear modulus $G_{\rm al}$ for the aluminum.



Ans: $G_{\rm al} = 4.31(10^3) \, \rm ksi$

SOLUTION

From the stress-strain diagram,

$$E_{al} = \frac{\sigma}{\epsilon} = \frac{70}{0.00614} = 11400.65 \text{ ksi}$$

When specimen is loaded with a 9 - kip load,

when specimen is loaded with a 9 - kip load,

$$\sigma = \frac{P}{A} = \frac{9}{\frac{\pi}{4}(0.5)^2} = 45.84 \text{ ksi}$$

$$\epsilon_{\text{long}} = \frac{\sigma}{E} = \frac{45.84}{11400.65} = 0.0040205 \text{ in./in.}$$

$$\epsilon_{\text{lat}} = \frac{d' - d}{d} = \frac{0.49935 - 0.5}{0.5} = -0.0013 \text{ in./in.}$$

$$V = -\frac{\epsilon_{\text{lat}}}{\epsilon_{\text{long}}} = -\frac{-0.0013}{0.0040205} = 0.32334$$

$$G_{\text{al}} = \frac{E_{at}}{2(1 + \nu)} = \frac{11.4(10^3)}{2(1 + 0.32334)} = 4.31(10^3) \text{ ksi}$$
Ans.

Ans.

R3-2.

The elastic portion of the tension stress-strain diagram for an aluminum alloy is shown in the figure. The specimen used for the test has a gage length of 2 in. and a diameter of 0.5 in. If the applied load is 10 kip, determine the new diameter of the specimen. The shear modulus is $G_{\rm al} = 3.8(10^3)$ ksi.



SOLUTION

$$\sigma = \frac{P}{A} = \frac{10}{\frac{\pi}{4}(0.5)^2} = 50.9296 \text{ ksi}$$

From the stress-strain diagram

$$E = \frac{70}{0.00614} = 11400.65 \text{ ksi}$$

$$\epsilon_{\text{long}} = \frac{\sigma}{E} = \frac{50.9296}{11400.65} = 0.0044673 \text{ in./in.}$$

$$G = \frac{E}{2(1 + \nu)}; \quad 3.8(10^3) = \frac{11400.65}{2(1 + \nu)}; \quad \nu = 0.500$$

$$\epsilon_{\text{lat}} = -\nu\epsilon_{\text{long}} = -0.500(0.0044673) = -0.002234 \text{ in./in.}$$

$$\Delta d = \epsilon_{\text{lat}} d = -0.002234(0.5) = -0.001117 \text{ in.}$$

$$d' = d + \Delta d = 0.5 - 0.001117 = 0.4989 \text{ in.}$$

$$The definition of the equation of$$

THE NOTE POLE

Ans: d' = 0.4989 in.

80 kN

3 m

80 KH

3-

A

220 mm

В

210 mm

R3–3.

The rigid beam rests in the horizontal position on two 2014-T6 aluminum cylinders having the *unloaded* lengths shown. If each cylinder has a diameter of 30 mm, determine the placement x of the applied 80-kN load so that the beam remains horizontal. What is the new diameter of cylinder A after the load is applied? $v_{al} = 0.35$.

SOLUTION

$\zeta + \Sigma M_A = 0;$ $F_B(3) - 80(x) = 0;$ $F_B = \frac{80x}{3}$	(1)
$\zeta + \Sigma M_B = 0;$ $-F_A(3) + 80(3 - x) = 0;$ $F_A = \frac{80(3 - x)}{3}$	(2)
Since the beam is held horizontally, $\delta_A = \delta_B$	
$\sigma = rac{P}{A}; \qquad \epsilon = rac{\sigma}{E} = rac{rac{P}{A}}{E}$	
$\delta = \epsilon L = \left(\frac{\frac{P}{A}}{E}\right) L = \frac{PL}{AE}$	acting ion web
$\delta_A = \delta_B; \qquad \frac{\frac{80(3 - x)}{3}(220)}{AE} = \frac{\frac{80x}{3}(210)}{AE}$	se mil Miled.
80(3 - x)(220) = 80x(210)	
x = 1.53 m	Ans.
From Eq. (2),	
$F_A = 39.07 \text{ kN}$	
$\sigma_A = \frac{F_A}{A} = \frac{39.07(10^3)}{\frac{\pi}{4}(0.03^2)} = 55.27 \text{ MPa}$	
$\epsilon_{\text{long}} = \frac{\sigma_A}{E} = -\frac{55.27(10^6)}{73.1(10^9)} = -0.000756$	
$\epsilon_{\text{lat}} = -\nu \epsilon_{\text{long}} = -0.35(-0.000756) = 0.0002646$	
$d'_A = d_A + d \epsilon_{\text{lat}} = 30 + 30(0.0002646) = 30.008 \text{ mm}$	Ans.

*R3-4.

The wires each have a diameter of $\frac{1}{2}$ in., length of 2 ft, and are made from 304 stainless steel. If P = 6 kip, determine the angle of tilt of the rigid beam AB.



SOLUTION

Equations of Equilibrium: Referring to the free-body diagram of beam AB shown in Fig. a,

 $\begin{aligned} & & +\Sigma M_A = 0; \\ & & +\Sigma M_A = 0; \\ & & + \uparrow \Sigma M_B = 0; \end{aligned} \qquad \begin{aligned} & F_{BC}(3) - 6(2) = 0 \\ & & F_{BC} = 4 \text{ kip} \\ & + \uparrow \Sigma M_B = 0; \\ & & 6(1) - F_{AD}(3) = 0 \\ & & F_{AD} = 2 \text{ kip} \end{aligned}$

Normal Stress and Strain:

$$\sigma_{BC} = \frac{F_{BC}}{A_{BC}} = \frac{4(10^3)}{\frac{\pi}{4}\left(\frac{1}{2}\right)^2} = 20.37 \text{ ksi}$$
$$\sigma_{AD} = \frac{F_{AD}}{A_{AD}} = \frac{2(10^3)}{\frac{\pi}{4}\left(\frac{1}{2}\right)^2} = 10.19 \text{ ksi}$$

Since $\sigma_{BC} < \sigma_Y$ and $\sigma_A < \sigma_Y$, Hooke's Law can be applied

at instructors $\sigma_{BC} = E\epsilon_{BC};$ 20.37 = 28.0(10³) ϵ_{BC} $\epsilon_{BC} = 0.7276(10^{-3})$ in,/in. $\sigma_{AD} = E\epsilon_{AD};$ 10.19 = 28.0(10³) ϵ_{AD} $\epsilon_{AD} = 0.3638(10^{-3})$ in./in.

Thus, the elongation of cables BC and AD are given by

$$\delta_{BC} = \epsilon_{BC} L_{BC} = 0.7276(10^{-3})(24) = 0.017462 \text{ in.}$$

$$\delta_{AD} = \epsilon_{AD} L_{AD} = 0.3638(10^{-3})(24) = 0.008731 \text{ in.}$$

Referring to the geometry shown in Fig. b and using small angle analysis,

$$\theta = \frac{\delta_{BC} - \delta_{AD}}{36} = \frac{0.017462 - 0.008731}{36} = 0.2425(10^{-3}) \operatorname{rad}\left(\frac{180^{\circ}}{\pi \operatorname{rad}}\right) = 0.0139^{\circ} \operatorname{Ans.}$$



R3–5.

The wires each have a diameter of $\frac{1}{2}$ in., length of 2 ft, and are made from 304 stainless steel. Determine the magnitude of force **P** so that the rigid beam tilts 0.015°.



SOLUTION

Equations of Equilibrium: Referring to the free-body diagram of beam *AB* shown in Fig. *a*,

 $\zeta + \Sigma M_A = 0; \qquad F_{BC}(3) - P(2) = 0 \qquad F_{BC} = 0.6667P$ $+ \uparrow \Sigma M_B = 0; \qquad P(1) - F_{AD}(3) = 0 \qquad F_{AD} = 0.3333P$

Normal Stress and Strain:

$$\sigma_{BC} = \frac{F_{BC}}{A_{BC}} = \frac{0.6667P}{\frac{\pi}{4} \left(\frac{1}{2}\right)^2} = 3.3953P$$
$$\sigma_{AD} = \frac{F_{AD}}{A_{AD}} = \frac{0.3333P}{\frac{\pi}{4} \left(\frac{1}{2}\right)^2} = 1.6977P$$

Assuming that $\sigma_{BC} < \sigma_Y$ and $\sigma_{AD} < \sigma_Y$ and applying Hooke's Law,

 $\sigma_{BC} = E\epsilon_{BC}; \qquad 3.3953P = 28.0(10^6)\epsilon_{BC} \quad \epsilon_{BC} = 0.12126(10^{-6})P$ $\sigma_{AD} = E\epsilon_{AD}; \qquad 1.6977P = 28.0(10^6)\epsilon_{AD} \quad \epsilon_{AD} = 60.6305(10^{-9})P$ Thus, the elongation of cables *BC* and *AD* are given by

$$\delta_{BC} = \epsilon_{BC} L_{BC} = 0.12126(10^{-6})P(24) = 2.9103(10^{-6})P$$
$$\delta_{AD} = \epsilon_{AD} L_{AD} = 60.6305(10^{-9})P(24) = 1.4551(10^{-6})P$$

Here, the angle of the tile is $\theta = 0.015^{\circ} \left(\frac{\pi \text{rad}}{180^{\circ}}\right) = 0.2618(10^{-3}) \text{ rad.}$ Using small angle analysis,

$$\theta = \frac{\delta_{BC} - \delta_{AD}}{36}; \qquad 0.2618(10^{-3}) = \frac{2.9103(10^{-6})P - 1.4551(10^{-6})P}{36}$$
$$P = 6476.93 \text{ lb} = 6.48 \text{ kip} \qquad \text{Ans.}$$

Since $\sigma_{BC} = 3.3953(6476.93) = 21.99$ ksi $< \sigma_Y$ and $\sigma_{AD} = 1.6977(6476.93) = 11.00$ ksi $< \sigma_Y$, the assumption is correct.



Ans.

Ans.

work and

R3-6.

The head H is connected to the cylinder of a compressor using six $\frac{3}{16}$ -in. diameter steel bolts. If the clamping force in each bolt is 800 lb, determine the normal strain in the bolts. If $\sigma_Y = 40$ ksi and $E_{\rm st} = 29(10^3)$ ksi, what is the strain in each bolt when the nut is unscrewed so that the clamping force is released?

SOLUTION

Normal Stress:

$$\sigma = \frac{P}{A} = \frac{800}{\frac{\pi}{4} \left(\frac{3}{16}\right)^2} = 28.97 \text{ ksi} < \sigma_{\gamma} = 40 \text{ ksi}$$

Normal Strain: Since $\sigma < \sigma_{\gamma}$, Hooke's law is still valid.

$$\epsilon = \frac{\sigma}{E} = \frac{28.97}{29(10^3)} = 0.000999$$
 in./in.

Dell OUBE BUNNING IN THE INTERNE all Photos and a start and is portied

will destroy the

If the nut is unscrewed, the load is zero. Therefore, the strain $\epsilon = 0$

£

Η

R3-7.

The stress-strain diagram for polyethylene, which is used to sheath coaxial cables, is determined from testing a specimen that has a gage length of 10 in. If a load P on the specimen develops a strain of $\epsilon = 0.024$ in./in., determine the approximate length of the specimen, measured between the gage points, when the load is removed. Assume the specimen recovers elastically.



SOLUTION

Modulus of Elasticity: From the stress-strain diagram, $\sigma = 2$ ksi when $\epsilon = 0.004 \text{ in./in.}$

$$E = \frac{2 - 0}{0.004 - 0} = 0.500(10^3) \text{ ksi}$$

Elastic Recovery: From the stress-strain diagram, $\sigma = 3.70$ ksi when $\epsilon = 0.024$ in./in.

Elastic recovery
$$= \frac{\sigma}{E} = \frac{3.70}{0.500(10^3)} = 0.00740$$
 in./in.

Permanent Set:

Permanent set =
$$0.024 - 0.00740 = 0.0166$$
 in./in.

Thus,

Permanent elongation = 0.0166(10) = 0.166 in.

 $L = L_0 + permanent elongation$

and is provide

un por courses (

= 10 + 0.166= 10.17 in.

Ans.

cludingon

*R3-8.

The pipe with two rigid caps attached to its ends is subjected to an axial force P. If the pipe is made from a material having a modulus of elasticity E and Poisson's ratio ν , determine the change in volume of the material.

SOLUTION

Normal Stress: The rod is subjected to uniaxial loading. Thus, $\sigma_{\text{long}} = \frac{P}{A}$ and $\sigma_{\text{lat}} = 0$.

$$\delta V = A\delta L + 2\pi r L\delta r$$

$$= A\epsilon_{\text{long}}L + 2\pi rL\epsilon_{\text{lat}}r$$

Using Poisson's ratio and noting that $AL = \pi r^2 L = V$,

* *

$$\delta V = \epsilon_{\text{long}} V - 2\nu \epsilon_{\text{long}} V$$
$$= \epsilon_{\text{long}} (1 - 2\nu) V$$
$$= \frac{\sigma_{\text{long}}}{E} (1 - 2\nu) V$$

* *

Since σ_{low} = P/A

Since
$$\sigma_{\text{long}} = T/A$$
,

$$\delta V = \frac{P}{AE} (1 - 2\nu) AL$$

$$= \frac{PL}{E} (1 - 2\nu)$$
Ans.

Ans:
$$\delta V = \frac{PL}{E} (1 - 2\nu)$$

Section a - a

C

R3-9.

The 8-mm-diameter bolt is made of an aluminum alloy. It fits through a magnesium sleeve that has an inner diameter of 12 mm and an outer diameter of 20 mm. If the original lengths of the bolt and sleeve are 80 mm and 50 mm, respectively, determine the strains in the sleeve and the bolt if the nut on the bolt is tightened so that the tension in the bolt is 8 kN. Assume the material at A is rigid. $E_{\rm al} = 70$ GPa, $E_{\rm mg} = 45$ GPa.

SOLUTION

Normal Stress:

$$\sigma_b = \frac{P}{A_b} = \frac{8(10^3)}{\frac{\pi}{4}(0.008^2)} = 159.15 \text{ MPa}$$
$$\sigma_s = \frac{P}{A_s} = \frac{8(10^3)}{\frac{\pi}{4}(0.02^2 - 0.012^2)} = 39.79 \text{ MPa}$$

Normal Strain: Applying Hooke's Law



Let all of an Part of the and their current and t and is ployde

will destroy the



Mechanics of Materials in SI Units Global Edition 10th Edition Hibbeler Solutions Manual © 2017 Pearson Education, Inc., Hoboken, NJ. All rights reserved. This material is protected under all copyright laws as they currently exist. Full Download: https://doi.org/10.1011/j.com/abchanics/product/imacchanics/pfingure/pfingure/product/imacchanics/pfingure/pfin

400 mm -

(a)

200 mm

Ans.

P = 2 kN

SWW

R3-10.

An acetal polymer block is fixed to the rigid plates at its top and bottom surfaces. If the top plate displaces 2 mm horizontally when it is subjected to a horizontal force P=2 kN, determine the shear modulus of the polymer. The width of the block is 100 mm. Assume that the polymer is linearly elastic and use small angle analysis.

SOLUTION

Normal and Shear Stress:

$$\tau = \frac{V}{A} = \frac{2(10^3)}{0.4(0.1)} = 50 \text{ kPa}$$

Referring to the geometry of the undeformed and deformed shape of the block shown in Fig. a, 200 mm

$$\gamma = \frac{2}{200} = 0.01$$
 rad

Applying Hooke's Law,

$$\tau = G\gamma;$$
 50(10³) = G(0.01)

G = 5 MPa

their courses will destroy the

Ans:
$$G = 5$$
 MPa